

## DESCRIPTION

PolySpec® LITE LATEX is a latex modified cement compound mixed with dry components to produce a versatile underlayment that bonds well to clean substrates without the aid of mechanical fasteners. It provides a strong, level, and seamless surface for finished deck coverings to adhere to.

LITE LATEX has been approved as meeting parts 2 and 6 of Annex 1 of the IMO Fire Testing Procedures Code. PolySpec® LITE LATEX is listed on the Federal Government's Qualified Products List under MIL-D-3135 Type II, Class I.

Coast Guard Approval Number 164.106/30/0

## TYPICAL APPLICATION

|             |  |
|-------------|--|
| • Primer    | LITE LATEX Slurry Coat                               |
| • Body Coat | 18.002 Emulsion and LITE LATEX Powder @ ¼" thickness |

## PERFORMANCE DATA

|  |  |
|--|--|
| Compressive Strength (ASTM C-306) .....                | 1,350 psi (wet)  |
| .....  | 1,380 psi (dry)  |
| Flexural Strength (ASTM C-580) .....                   | 1,200 psi  |
| Moisture Absorption (MIL-D-3135) .....                 | .2.15%   |
| Impact Resistance (MIL-D-3135) .....                   | 0.031" – No chipping   |
| Indentation (MIL-D-3135) .....                         | Initial: 24 hrs cure – <20% max                                      |
| .....  | Residual: 96 hrs cure – 5% max                                       |
| Corrosion Resistance (MIL-D-3135) .....                | No signs of corrosion  |
| Oil Absorption (MIL-D-3135) .....                      | 1.7%   |
| Adhesive Strength (MIL-D-3135) .....                   | 195 psi  |
| Fire Resistance (IMO Res.A.687(17)) .....              | Not readily ignitable  |
| Resistance to Elevated Temperatures (MIL-D-3135) ..... | No flow, no slip,<br>no softening                                    |
| Shock Resistance (MIL-D-3135) .....                    | No signs of chipping, cracking or<br>detachment from the steel plate |

## STORAGE & INSTALLATION

|  |                             |
|--|-----------------------------|
| Storage Environment .....                | Dry area, 65–80°F           |
| Application Temperature, ambient .....   | 50–85°F                     |
| Application Temperature, substrate ..... | Minimum 5°F above dew point |
| Service Temperature .....                | Maximum 150°F               |
| Shelf Life .....                         | 12 months                   |
| Pot Life, @ 77°F .....                   | 30 minutes                  |
| Foot Traffic, @ 77°F .....               | 12-16 hours                 |
| Full Service, @ 77°F .....               | 18-24 hours                 |

*Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.*

## CONSIDERATIONS & LIMITATIONS

1. Prepare substrate according to "Surface Preparation" portion of this document.
2. This product should be used in dry spaces only, unless otherwise instructed by a PolySpec representative.
3. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
4. For industrial/commercial use. Installation by trained personnel only.

# PolySpec® LITE LATEX

## TECHNICAL DATA SHEET

### Light Weight Polymer Modified Underlayment

## BENEFITS

- Zero VOC's, very low odor
- Lightweight
- Fast -setting
- Can be feather-edged
- Produces a smooth finish
- Compatible with most adhesives

## RECOMMENDED USES

- Leveling and fairing uneven floors and welds
- Ramp between floors of different elevations, creating a pitch to drain
- Underlayment for resilient flooring, vinyl, ceramic tile, carpet and other flooring materials

## GENERIC DESCRIPTION

Latex Modified Cementitious Underlayment

## PACKAGING / COVERAGE

### Primer

|                   |                              |
|-------------------|------------------------------|
| 18.002 Emulsion   | 5-Gallon Unit / 1000 sq. ft. |
| Lite Latex powder | 50-Pound bag / 300 sq. ft.   |

### Body Coat @ ¼" thickness:

|                   |                             |
|-------------------|-----------------------------|
| 18.002 Emulsion   | 5-Gallon Unit / 150 sq. ft. |
| Lite Latex powder | 50-Pound bag / 25 sq. ft.   |

## SURFACE PREPARATION

**Steel:** For steel surfaces, a “Near White Metal” ultra high-pressure wash or abrasive blast with anchor profile of 2–4 mils in accordance with Steel Structures Painting Council Specification SP-10 or NACE No. 2 is required.

*This product can be applied to the following substrate(s) that have been prepared according to PolySpec Surface Preparation Guidelines:*

Existing deck covering shall be totally removed. It is imperative that, before installation begins, all surfaces to which PolySpec decking product(s) will be applied — including deck, bulkheads, pipes, protrusions, etc. — are cleaned of all foreign matter such as dirt, dust, plaster, cement, paint, oil, grease, wax, rust, scale, moisture, concrete curing compounds or release agents, and other contamination.

- *Metal surfaces must be cleaned until bright metal is exposed.*
- *Surface preparation should include vertical surfaces three inches up from the deck.*
- *Surface preparation shall be by the methods most feasible, such as grinding, abrasive vacuum blasting, sanding, or using a needle gun or other appropriate hand tool(s) to clean the deck.*
- *Remove all dust and other loose material so that adhesion is assured.*

If existing substrate or deck covering cannot be removed, material must be cleaned and inspected for soundness prior to installing PolySpec product.

If PolySpec product is to be installed over an existing system, it is imperative that the coating be thoroughly sanded, cleaned and wiped with isopropyl alcohol before installation of the PolySpec decking product(s).

Urethane topcoats must be completely removed to ensure adhesion of the system.

**Refer to PolySpec Surface Preparation Guidelines for more details.**

## INSTALLATION STEPS

1. **Primer Application:** Pre-mix approximately 3 parts 18.002 Emulsion with 1 part LITE LATEX powder. Apply as a slurry to the deck with a heavy bristle brush. This process should wet the floor with the emulsion powder slurry completely. Body coat should be troweled into the wet primer coat. If primer coat dries prior to body coat placement, re-apply primer slurry. This process is the key to good surface adhesion and is integral to a successful application
2. **Body Coat Application:** Mix thoroughly 3/4 gallon of 18.002 Latex Liquid with one 50 lb. bag of LITE LATEX Powder. Vary mix according to needs. Thin coats use a wetter mix. Thick coats use a drier mix. Pour 3/4 gallon of the 18.002 Latex Liquid into a clean 10-gallon container. Gradually add one 50 lb. bag of LITE LATEX Powder to the liquid. Use a 3/4-inch drill and mixing paddle.

*Note: PolySpec LITE LATEX is fast setting. Working time of the mixed material is approximately 30 minutes. Mix no more than can be conveniently applied within that time frame.*

A hoe and mortar box can also be used. If using this method, pour the liquid into one end of the mortar box and the powder into the other end. Gradually cut the powder into the liquid using the hoe. With either method be sure to get a homogenous mix making sure that no dry particles remain.

While the surface wetting coat is still wet, trowel on the underlayment body coat with a steel trowel. Do not over-trowel, but use a smooth, sweeping motion. Curing time is approximately 12 hours, although curing time will vary with temperature and humidity. Be sure that material is completely dry before application of finish deck covering.

3. **Sanding:** When PolySpec LITE LATEX serves as the underlayment for resilient tile, it is generally desirable to lightly sand the surface to remove trowel marks. This can be done after the underlayment has cured approximately 12 hours.
4. **Curing:** PolySpec LITE LATEX may be covered with a resilient flooring system, or other desired finish flooring system, immediately after sanding and after it has been vacuumed to pick up dust. If it is to be covered without sanding, an overnight curing period is required. If the finished deck coating is a trowel applied material, the LITE LATEX system should be allowed to cure for one or two days (depending on drying conditions) to make certain that it is thoroughly dry.

C / DOC LITELATEX 04004-0206-TDS

Rev 1106

TuffRez and PolySpec are ® Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

TuffRez and PolySpec are ® Registered Trademarks of PolySpec L.P. © Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.