

DESCRIPTION

PolySpec® TWEDE 41 is a decorative quartz broadcast decking system, combining a clear 100% solids epoxy resin binder with color quartz aggregates, and sealed with clear epoxy finish coats. The color quartz aggregate is composed of spherical, translucent particles coated with a pigmented film. They can be combined in various colors to provide a seamless, low maintenance surface with a pleasing, textured appearance.

PolySpec® TWEDE 41 is on the Federal Government’s Qualified Products List under MIL-D-24613, Type I, Class I.

TYPICAL APPLICATION

Table with 2 columns: Application Item, Thickness/Quantity. Rows include Receiving Coat(s), Broadcast, Seal Coat, and Polyurethane Topcoat.

PERFORMANCE DATA

Table listing performance metrics such as Compressive Strength, Tensile Strength, Flexural Strength, Water Absorption, Impact Resistance, Indentation, Adhesion, Oil Absorption, Thermal Compatibility, and Fire Resistance.

Non-Slip Properties (ASTM D-2047) ... >0.6 (Will vary with selected finish)
Abrasion Resistance 1000 gram load 1000 cycles CS-17 wheels <.060 gm loss

STORAGE & INSTALLATION

Table listing storage and installation parameters: Storage Environment, Application Temperature (ambient and substrate), Service Temperature, Shelf Life, Pot Life, Foot Traffic, Full Service.

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life.

CONSIDERATIONS & LIMITATIONS

- 1. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
2. Do not thin with solvents unless advised to do so by PolySpec.
3. Confirm product performance in specific chemical environment prior to use.
4. Prepare substrate according to "Surface Preparation" portion of this document.

PolySpec® TWEDE 41

TECHNICAL DATA SHEET

Decorative Quartz Broadcast Seamless Floor

BENEFITS

- Requires no waxing or stripping
• Available in a wide variety of color combinations
• Fire retardant
• Good non-slip properties
• Excellent impact resistance
• Available with waterproof membrane

RECOMMENDED USES

- Corridors
• Toilet areas
• Auditoriums
• Cafeterias
• Laboratories
• Mechanical equipment rooms
• Change rooms

GENERIC DESCRIPTION

Quartz Broadcast Epoxy Floor

STANDARD COLORS

Please refer to the Polyspec Decorative Quartz color chart for TWEDE blends available

PACKAGING / COVERAGE

Table showing packaging and coverage for Receiving Coat(s), Broadcast Quartz, Seal Coat, and Optional Top Coat.



5. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
6. For industrial/commercial use. Installation by trained personnel only.

SURFACE PREPARATION

Steel: For steel surfaces, a “Near White Metal” ultra high-pressure wash or abrasive blast with anchor profile of 2–4 mils in accordance with Steel Structures Painting Council Specification SP-10 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details.

INSTALLATION STEPS

1. **Priming (Optional):** When installing over bare steel, a primer (such as PolySpec® TITE M-50) will be required.

PolySpec® TITE M-50: Using a Jiffy mixer blade and a 1/4" variable speed drill, thoroughly mix four Parts A and one Part B together for 1–2 minutes. Scrape the sides and bottom of the can to be sure that all material is thoroughly mixed together. Apply to the deck at 4–5 mils using a short nap roller. Coverage will be 200–250 square feet per gallon. Allow to cure for 10–12 hours at 75°F (25°C).

2. **1st Receiving Coat – Self Priming:** All products must be used promptly once the hardener has been added to the resin to avoid having the material set up in the container. Mix Part B (710) Resin into Part A (700) Curing Agent using a jiffy style mixer and ¼" variable speed drill thoroughly for 1-2 minutes. Scrape the sides and bottom of the can to insure complete mixing.

Apply 700/710 with squeegee or spring trowel. Back roll with 3/8" nap roller to a uniform thickness of approximately 16 mils. Broadcast decorative granules to dry appearance. It is very important that no wet areas are left during the curing process. Puddling will cause smooth areas in the finish floor. Allow to cure 10–12 hours @ 75°F (24°C). Sweep or vacuum all loose granules from surface.

3. **2nd Receiving Coat:** Workers should wrap their shoes in polyethylene, masking tape or other suitable covering to protect the surface (or remove shoes). Mix Part B (710) into Part A (700) using a jiffy style mixer and ¼" variable speed drill thoroughly for 1-2 minutes. Apply 700/710 with squeegee or spring trowel. Broadcast decorative granules to dry appearance making sure to leave no visible puddles. Allow to cure 8-10 hours @ 75°F (24°C). Sweep or vacuum all loose granules. Scrape with trowel or lightly sand to remove any partially adhered granules.
4. **1st Seal Coat:** Workers should wrap their shoes in polyethylene, masking tape or other suitable covering to protect the surface (or remove shoes). It is acceptable to use spike shoes during the application. Mix Part B (710) into Part A (700) using a jiffy style mixer and ¼" variable speed drill thoroughly for 1-2 minutes. Apply 700/710 with squeegee or spring trowel. Back roll with 3/8" nap, phenolic core roller to remove any lap marks and bring grout coat to a uniform appearance. Allow to cure 8–10 hours @ 75°F (24°C).
5. **2nd Seal Coat:** Mix Part B (710) into Part A (700) using a jiffy style mixer and ¼" variable speed drill thoroughly for 1-2 minutes. Apply 700/710 with squeegee or spring trowel. Back roll with 3/8" nap, phenolic core roller to remove any lap marks and bring grout coat to a uniform appearance. Use spiked shoes while rolling. Allow to cure 24 hours @ 75°F (24°C) before opening to foot traffic.
6. **Top Coat (Optional):**
 - a) Apply PolySpec® 1757 Flat Finish Epoxy for a durable matte finish.
 - b) Apply FLEX FR urethane Top Coat (TuffRez 236) for a durable satin finish.

Please refer to separate Technical Data Sheets for Installation Instructions for the above products.

Note: All liquids should be mixed with a low speed (300 rpm) drill and jiffy blade for 1-½ minutes per batch.

C / DOCTWEDE 41 04009-0206-TDS

Rev 11/06

TuffRez and PolySpec are ® Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.