

DESCRIPTION

PermaRez 345S Saturant is a polymeric topcoat to the PermaRez 345 Crack- Bridging Chemical Resistant Composite Lining System. It is used as a saturant and bond coat to incorporate fiberglass reinforcement into the system, giving the system tensile strength between the elastomeric membrane and the chemical resistant topcoats. PermaRez 345 Saturant also serves as a bond coat for other PolySpec chemical resistant coatings.

TYPICAL APPLICATION

• Primer	PolySpec 300EX @ 5–7 mils (concrete) or PolySpec TITE M-50 @ 4–5 mils (steel)
• Membrane	PermaRez 345M @ 30–50 mils
• Receiving Coat	PermaRez 345S @ 20 mils
• Fabric	Type M (1.5 oz mat)
• Saturant	PermaRez 345S @ 15–20 mils
• Topcoat	Variety of topcoats available

PERFORMANCE DATA

Compressive Strength (ASTM C-579)	10,000 psi
Tensile Strength (ASTM D-412)	2,000 psi
Bond Strength (ASTM D-4541)	Concrete Failure

STORAGE & INSTALLATION

Storage Environment	Dry area, 65–80°F
Application Temperature, ambient	50–95°F
Application Temperature, substrate	Minimum 5°F above dew point
Shelf Life	6 months
Pot Life, @ 77°F	45 minutes
Set Time, @ 77°F	16 hours

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

CONSIDERATIONS & LIMITATIONS

1. For best results, work area should be humidity and temperature controlled.
2. Do not thin with solvents unless advised to do so by PolySpec.
3. Confirm product performance in specific chemical environment prior to use.
4. Prepare substrate according to “Surface Preparation” portion of this document.
5. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
6. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
7. For industrial/commercial use. Installation by trained personnel only.

PermaRez[®] 345S

TECHNICAL DATA SHEET

Crack-Bridging Lining— Saturant, Chemical Resistant

BENEFITS

- Low viscosity, penetrates fiberglass for easy saturation
- Can be topcoated with vinyl ester, polyester or epoxy coatings
- Increased abrasion resistance
- Used with PermaRez 345 Membrane, provides tough stress relieving membrane on which chemical resistant coating systems are applied

RECOMMENDED USES

- Chemical processing floor areas
- Drum storage pads
- Secondary containment
- Trenches and sumps
- Truck loading/unloading areas
- Concrete clarifiers

GENERIC DESCRIPTION

Epoxy Urethane

STANDARD COLORS

Amber

PACKAGING

3-Gallon Unit

COVERAGE

30 ft² / gallon @ 40 mils
(Includes one 20 mil coat and saturant)

SURFACE PREPARATION

Concrete: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.*
- *All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.*
- *Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*

Steel: For steel surfaces, a “Near White Metal” ultra high-pressure wash or abrasive blast with anchor profile of 2–4 mils in accordance with Steel Structures Painting Council Specification SP-10 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details.

INSTALLATION STEPS

NOTE: PermaRez 345S Saturant is normally applied over PermaRez 345M Membrane. See data sheet for installation details.

1. Pour Component B Hardener into Component A Resin. Mix thoroughly using a jiffy-type mixer operated at low speed until a uniform blend is attained. Scrape the sides of the pail to ensure the product has been properly mixed; any unmixed material left on the side of the pail will not cure.
2. Apply a thin coat of PermaRez 345 Saturant, approximately 20 mils, by roller or squeegee over the PermaRez 345 Membrane.
3. Lay in fiberglass mat reinforcement, overlapping the edges by 1–2 inches.
4. Apply additional PermaRez 345 Saturant Resin and roll out fiberglass until the whiteness of the glass disappears. Roll out with a serrated roller to remove any entrapped air.
5. Allow to cure (approximately 16 hours at 77°F) before proceeding.
6. Normally, the application of the topcoat can proceed without further surface preparation.

When applying a polyester or vinyl ester topcoat, allow for saturant to cure a minimum of 72 hours. Wash the surface with soap and water before proceeding. Allow to thoroughly dry.

NOTE: If the saturant becomes very hard due to extended cure time, lightly sand the surface before applying topcoat.

7. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

1.6R: 1H / DOC PR345S-TDS

Rev 03/05

PermaRez and PolySpec are © Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.