

## DESCRIPTION

PolySpec 193, a high performance, 100% solids semi-rigid epoxy control joint filler, is formulated for applications requiring a combination of resiliency and tensile strength. Because of its high strength-to-flexibility ratio, it minimizes the spalling effects of forklifts and small hard wheel traffic on joint edges. PolySpec 193 is offered in two grades: Pourable (for horizontal surfaces) and Paste (non-sag for vertical and overhead surfaces).

## PERFORMANCE DATA

Compressive Strength (ASTM C-579) .....	800–850 psi
Tensile Strength (ASTM C-412) .....	850–1,050 psi
Adhesion Strength (ASTM D-4541) .....	500–600 psi
Hardness, Shore D (ASTM D-2240) .....	45–55
Hardness, Shore A (ASTM D-2240) .....	90–100
C-Tear, lbs/in (ASTM D-624) .....	100–150
Volume Solids .....	100%

## STORAGE & INSTALLATION

Storage Environment .....	Dry area, 65–80°F
Application Temperature, ambient .....	50–95°F
Application Temperature, substrate .....	Minimum 5°F above dew point
Shelf Life .....	6 months
Pot Life, @ 77°F .....	25–30 minutes
Foot Traffic, @ 77°F .....	4 hours
Full Service, @ 77°F .....	24 hours

*Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.*

## CONSIDERATIONS & LIMITATIONS

1. This product is recommended for indoor joint sealing applications.
2. For overhead applications, use PolySpec 193 Paste grade.
3. Do not thin with solvents unless advised to do so by PolySpec.
4. Confirm product performance in specific chemical environment prior to use.
5. Prepare substrate according to “Surface Preparation” portion of this document.
6. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
7. For industrial/commercial use. Installation by trained personnel only.

# PolySpec® 193

## TECHNICAL DATA SHEET

# Epoxy Control Joint Sealant, Semi-Rigid

## BENEFITS

- Superior adhesion when compared to polyureas
- Withstands steel wheel vehicular traffic
- Flexible epoxy prevents age hardening
- High resistance to penetration
- Limits joint deflection
- Protects control joints and saw cuts from deterioration
- Inert micro-fibers serve as reinforcing bars that strengthen sealant even as it moves under load

## RECOMMENDED USES

- Warehouse floors & docks
- Convention centers, exhibition halls & stadiums
- Mechanical assembly bays with heavy foot and vehicular traffic
- Vertical and overhead surfaces

## GENERIC DESCRIPTION

Polysulfide-Modified Epoxy Sealant

## STANDARD COLORS

Gray

## PACKAGING

2-Gallon Unit

AVAILABLE IN POURABLE OR PASTE (NON-SAG) GRADE

## COVERAGE

JOINT SIZE	COVERAGE PER UNIT
1/2" W x 1/4" D .....	154 linear ft
1/2" W x 3/8" D .....	102 linear ft
3/4" W x 3/8" D .....	68 linear ft
3/4" W x 1/2" D .....	51 linear ft
1" W x 1/2" D .....	38 linear ft
1" W x 3/4" D .....	25 linear ft

## SURFACE PREPARATION

**Concrete:** Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Blow joint with compressed air to remove dust, standing water and other potential contaminants.*

**Refer to PolySpec Surface Preparation Guidelines for more details.**

## INSTALLATION STEPS

1. Tape all sloping joints. Apply a backer rod or other type of bond breaker into the joint, if applicable.

*NOTE: Ideally, the joint depth should be one half the joint width.*

2. Pour (pourable grade) or scoop (paste grade) Component A Resin and Component B Hardener into a separate clean mixing pail. Mix well with a mechanical jiffy-type mixer operated at low speed for 3–5 minutes, or until uniform in color.

*NOTE: Do not dilute or alter TuffRez 193. Mix entire contents of kit.*

3. **Pourable Grade:** Pour into joint using a pour can with a spout suited for the joint size.

**Paste Grade:** Trowel mixed material into joint.

*NOTE: For best results, apply when the application temperature is closest to the mean temperature for the area.*

4. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

1R:1H / DOC PS193-TDS

Rev 03/05

RezRok and PolySpec are © Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.