

## DESCRIPTION

PolySpec® Ultra is a two-component, high gloss acrylic aliphatic polyurethane coating designed for industrial maintenance applications. It is suited for use as a topcoat over an epoxy system or alone over primed floor surfaces.

## TYPICAL APPLICATION

• Primer	PolySpec or TuffRez Epoxy Primer @ 5–7 mils
• Basecoat	Epoxy Basecoat from PolySpec @ 15–20 mils (various coatings available)
• Topcoat	PolySpec Ultra @ 4–6 mils WFT
• Options	Non-Skid Grit (0.5 to 1.0 lb/gal)

## PERFORMANCE DATA

Compressive Strength (ASTM C-579) .....	12,900 psi
Tensile Strength (ASTM D-638) .....	5,300 psi
Flexural Strength (ASTM C-580) .....	5,351 psi
Hardness, Shore D (ASTM D-2240) .....	70–75
Bond Strength (ASTM D-4541) .....	300 psi
Abrasion Resistance (ASTM D-4060) .....	30 mg
VOC .....	2.8 lbs/gal; 335 gm/L
Volume Solids .....	65%

## STORAGE & INSTALLATION

Storage Environment .....	Dry area, 65–80°F
Application Temperature, ambient .....	55–90°F
Application Temperature, substrate .....	Minimum 5°F above dew point
Shelf Life .....	6 months
Pot Life, @ 77°F .....	25 minutes
Foot Traffic, @ 77°F .....	12 hours
Full Service, @ 77°F .....	24 hours

*Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.*

## CONSIDERATIONS & LIMITATIONS

1. This product produces a smooth surface and will be slippery when wet. Non-skid grit may be added for slip resistance.
2. Vehicles with rubber tires should not be parked on coating within 72 hours of installation.
3. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
4. Do not thin with solvents unless advised to do so by PolySpec.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to “Surface Preparation” portion of this document.
7. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
8. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
9. For industrial/commercial use. Installation by trained personnel only.

# PolySpec® Ultra

## TECHNICAL DATA SHEET

# Polyurethane Coating, High Gloss, UV Stable

## BENEFITS

- Non-flammable per D.O.T. classification
- Excellent gloss and color retention
- Non-yellowing, UV stable formula
- Good exterior durability
- Resists attack by most acids, alkali, detergents, lubricating oils, solvents and chemicals
- Good abrasion resistance

## RECOMMENDED USES

- Aircraft hangars
- Automotive service bays
- Warehouse floors
- Manufacturing areas
- Automobile dealer showrooms

## GENERIC DESCRIPTION

Acrylic Aliphatic Polyurethane

## STANDARD COLORS

Clear

Light Gray, Sand, White

COLOR PACKS SOLD SEPARATELY; SEE MIX RATIOS ON NEXT PAGE

Additional colors available upon request. Non-stocking colors may be subject to additional lead time, minimum order requirements, and a slight premium.

## PACKAGING

3-Gallon Unit

Color Packs, Urethane (sold separately)

1-Quart Unit or 9-Unit Case

## COVERAGE

275–300 ft<sup>2</sup>/gallon @ 4–6 mils WFT

## SURFACE PREPARATION

**Concrete:** Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.*
- *All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.*
- *Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*

**Refer to PolySpec Surface Preparation Guidelines for more details.**

## INSTALLATION STEPS

1. PolySpec® Ultra is normally applied over a PolySpec® or TuffRez® Epoxy Primer or as a finish coat over a TuffRez® epoxy floor coating system. See applicable data sheets for detailed installation instructions of these products.

*NOTE: For use as a topcoat for TuffRez® epoxy coatings, apply within 24 hours of epoxy installation. If 24 hours has passed, sand the coating and wipe with a 50:50 mixture of water and isopropanol. Once solvent has flashed, proceed with application of PolySpec Ultra.*

2. Component A should be premixed prior to using due to possible additive separation that may occur during transportation and storage.
3. OPTIONAL STEP: For color versions, premix the color pack(s) for 1–2 minutes. Then, mix the color pack(s) into Component A until uniform color is attained.

COLORS & MIX RATIOS Color Pack, Urethane	Qty of Color Packs per 3-Gallon Unit
• 600 White	2
• 610 Light Gray	1
• 670 Sand	2

*NOTE: Containers are filled by weight, not by volume. Amount of pigment in 1-quart container will vary according to color.*

*NOTE: Use only PolySpec color packs labeled for use with Urethane.*

4. Pour Component B Hardener into the Component A Resin pail and mix well with a mechanical jiffy-type mixer operated at low speed. Scrape the side of the pail to ensure the entire product has been properly mixed; any unmixed material left on the side of the pail will not cure.

*NOTE: Do not turn the pail upside down and allow to drain onto substrate.*

5. OPTIONAL STEP: Add 0.5 to 1.0 pound of non-skid grit to catalyzed coating for increased wear resistance. Mix well.

*NOTE: The addition of non-skid grit will reduce gloss level.*

6. Apply by dip and roll method, using a short-nap roller or squeegee (short-nap roller recommended if non-skid grit has been added to the coating mixture) and back-roll. To prevent lap lines in finish coat, immediately cross roll material (uniform 90° angle to initial coat).

7. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

C / DOC ULTRA-TDS

Rev 09/07

TuffRez and PolySpec are ® Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.