

## DESCRIPTION

TuffRez 200FS is a fast-setting, heavy-duty polymer resin and aggregate floor surfacer intended for jobs where downtime is limited. Applied at 1/8 to 1/4", this durable system is suited for floors subjected to chemical exposure and mechanical abuse. It is commonly utilized for new construction as a protective overlay or for renovation work to restore surfaces; it can also be used as a cove base.

## TYPICAL APPLICATION

• Primer Coat	PolySpec or TuffRez Epoxy Primer @ 5–7 mils
• Mortar Coat	TuffRez 200FS with F-3 Powder @ 1/4"
• Grout Coat	TuffRez 200FS @ 125–250 ft <sup>2</sup> /gal
• Options	TuffRez or NovoRez Topcoat Non-Skid Grit Anti-Microbial Formulation Upgrade (TuffRez 200FS-AM)

## PERFORMANCE DATA

Compressive Strength (ASTM C-579)	10,550 psi
Tensile Strength (ASTM C-307)	1,800 psi
Flexural Strength (ASTM C-580)	4,000 psi
Hardness, Shore D (ASTM D-2240)	84–94
Bond Strength (ASTM D-4541)	425 psi
Abrasion Resistance (ASTM D-4060)	79 mg
VOC	0.23 lb/gal; <30 gm/L
Volume Solids	>95%

## STORAGE & INSTALLATION

Storage Environment	Dry area, 65–80°F
Application Temperature, ambient	50–95°F
Application Temperature, substrate	Minimum 5°F above dew point
Shelf Life	1 year
Pot Life, @ 77°F	20 minutes
Foot Traffic, @ 77°F	4 hours
Full Service, @ 77°F	12–24 hours

*Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.*

## CONSIDERATIONS & LIMITATIONS

1. This product is not designed for exterior use, immersion, or any use where moisture can reach the underside of the flooring.
2. PolySpec recommends the use of a slip resistant grit with this product.
3. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
4. Do not thin with solvents unless advised to do so by PolySpec.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to "Surface Preparation" portion of this document.
7. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
8. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
9. For industrial/commercial use. Installation by trained personnel only.

# TuffRez<sup>®</sup> 200FS

## TECHNICAL DATA SHEET

### Epoxy Topping Binder, Fast Set

## BENEFITS

- Minimizes downtime and reduces cost by improving crew installation efficiency/time
- More blush resistant than typical fast-setting epoxy coatings
- Superior trowelability
- Seamless, monolithic application; no crevices where dirt and bacteria can dwell
- Excellent impact and abrasion resistance
- Resistant to many acids, alkalis and salts

## RECOMMENDED USES

- Chemical processing plants
- Food & beverage plants
- Manufacturing facilities
- Animal holding areas
- Laboratories
- Assembly lines
- Traffic aisles

## GENERIC DESCRIPTION

Modified Epoxy

## STANDARD COLORS

Clear

Solid Colors: See "Color Packs, Epoxy"

## PACKAGING

15-Gallon Unit

*F-3 Powder sold separately in 50 pounds bags; 23 bags needed per 15-Gallon Unit*

## COVERAGE

Mortar Coat (1 gal. binder + 75 lb. F-3 powder):  
33 ft<sup>2</sup> / gallon @ 1/4 inch

Grout Coat:  
125–250 ft<sup>2</sup> / gallon

## SURFACE PREPARATION

**Concrete:** Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.*
- *All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.*
- *Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*

**Refer to PolySpec Surface Preparation Guidelines for more details.**

## INSTALLATION STEPS

1. Prime surface with a PolySpec or TuffRez Primer for epoxies on concrete surfaces. See data sheet for application details.

### *Mortar Coat*

2. Component A Resin should be premixed prior to use due to possible separation that may occur during transportation and storage.
3. Combine Component A Resin and Component B Hardener in a separate mixing vessel. Mix with a mechanical jiffy-type mixer operated at low speed.
4. OPTIONAL STEP: For cove base, mix fumed silica thixotrope into resin/hardener mixture until desired consistency is achieved. Trowel into place.
5. Pour catalyzed liquid into a concrete or mortar mixer. Add F-3 powder (75 lbs per gallon of binder) and mix thoroughly until all particles are wetted out.
6. Apply mortar coat with a screed box or a rake set at the appropriate height. Trowel smooth using a power trowel or a steel finishing trowel.

### *Grout Coat*

7. Sand the surface to remove any trowel marks or imperfections.
8. Repeat steps 2 and 3 above to prepare grout coat mixture.
9. Apply a grout coat by pulling a trowel tightly over the surface at a coverage rate of approximately 125–250 ft<sup>2</sup>/gallon. The grout coat should fill any slight voids or surface imperfections and provide a smooth finish.

### *Optional Topcoat*

10. Apply one or two topcoats of selected coating as needed for chemical resistance. Introduce non-skid grit into the topcoats for additional slip resistance.

### *Cleaning*

11. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

2R:1H / DOC TR200FS-TDS

Rev 01/10

TuffRez, NovoRez and PolySpec are © Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at [www.polyspec.com](http://www.polyspec.com) for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

**PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.**

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.