

DESCRIPTION

TuffRez 201TC is a two component, 100% solids, medium viscosity epoxy topcoat used with decorative quartz flooring systems.

TYPICAL APPLICATION

• Primer	PolySpec or TuffRez Epoxy Primer @ 5–7 mils
• Receiving Coat	TuffRez 201RC @ 20 mils
• Decorative Quartz	0.6 lbs/ft ²
• Topcoat	TuffRez 201TC @ 16 mils Anti-Microbial Formulation Upgrade (TuffRez 201TC-AM)

PERFORMANCE DATA

Compressive Strength (ASTM C-579)	9,200 psi
Tensile Strength (ASTM D-638)	1,650 psi
Flexural Strength (ASTM C-580)	4,000 psi
Hardness, Shore D (ASTM D-2240)	85–90
Bond Strength (ASTM D-4541)	425 psi
Abrasion Resistance (ASTM D-4060)	80 mg
Volume Solids	100%

STORAGE & INSTALLATION

Storage Environment	Dry area, 65–80°F
Application Temperature, ambient	50–95°F
Application Temperature, substrate	Minimum 5°F above dew point
Shelf Life	1 year
Pot Life, @ 77°F	35 minutes
Set Time, @ 77°F	10–12 hours
Service, @ 77°F	Light: 24 hours / Full: 48–72 hours

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

CONSIDERATIONS & LIMITATIONS

1. Due to viscosity, this product will follow contours of substrate. Floor should be planed and leveled. If this cannot be achieved, PolySpec recommends TuffRez[®] DL-2 System, which incorporates TuffRez[®] 201 Epoxy Floor Coating.
2. Do not use partial units. Prolonged exposure of product in containers to air may cause loss of clarity.
3. This product is not designed for exterior use, immersion, or any use where moisture can reach the underside of the flooring.
4. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
5. Do not thin with solvents unless advised to do so by PolySpec.
6. Confirm product performance in specific chemical environment prior to use.
7. Prepare substrate according to “Surface Preparation” portion of this document.
8. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
9. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
10. For industrial/commercial use. Installation by trained personnel only.

TuffRez[®] 201TC

TECHNICAL DATA SHEET

Epoxy Topcoat, Medium Viscosity Gloss

BENEFITS

- Allows for single grout coat / topcoat
- Combined with TuffRez 201RC as a base coat, creates effect of a much thicker application with fewer and less costly steps
- Seamless, monolithic flooring
- Resists many acids, alkalies and salts

RECOMMENDED USES

- Laboratories, hospitals, healthcare facilities
- Stadiums & other entertainment venues
- Educational & institutional facilities
- Cafeterias, storefronts, aisles
- Bathrooms, showers

GENERIC DESCRIPTION

Epoxy

STANDARD COLORS

Clear

PACKAGING

15-Gallon Unit

COVERAGE

100 ft² / gallon @ 16 mils

SURFACE PREPARATION

Concrete: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.*
- *All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.*
- *Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*

Refer to PolySpec Surface Preparation Guidelines for more details.

INSTALLATION STEPS

1. Install primer, base coat and broadcast decorative quartz system with TuffRez 201 or TuffRez 201RC per installation procedures listed on the product's technical data sheet.
2. Pour Component A Resin and Component B Hardener into a separate mixing vessel and mix with a mechanical jiffy-type mixer operated at low speed.
3. Apply one to two topcoats of resin/hardener mixture by roller or notched trowel to surface. Two topcoats will provide a smooth, high gloss finish. Lightly back roll material to ensure uniform coverage.

NOTE: DO NOT OVER ROLL. Too much rolling will introduce small air bubbles into system.

NOTE: As an alternative for the final topcoat, PolySpec offers a diverse line of epoxy and CRU topcoats for enhanced resistance to UV exposure, chemicals, abrasive wear, and other performance requirements. Please refer to PolySpec's online catalog at www.polyspec.com or contact PolySpec or an Authorized Representative.

4. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

2R-1H / DOC TR201TC-TDS

Rev 03/05

TuffRez and PolySpec are ® Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.