

DESCRIPTION

TuffRez 212 is a unique, two-component hybrid polymer coating designed to cure at extremely low temperatures. Derived from a product development program for Siberian environmental conditions, TuffRez 212 has the unique ability to cure in low mil thicknesses and without the odor problems associated with mercaptans or methacrylates.

TYPICAL APPLICATION

• Primer (optional)	PolySpec Primer @ 5–7 mils
• Base Coat	TuffRez 212 @ 20 mils
• Options	Non-Skid Grit @ 0.6 lbs/ft ² Anti-Microbial Formulation Upgrade (TuffRez 212-AM)

PERFORMANCE DATA

Compressive Strength (ASTM C-579)	14,900 psi
Tensile Strength (ASTM D-638)	1,200 psi
Flexural Strength (ASTM C-580)	17,400 psi
Hardness, Shore D (ASTM D-2240).....	56
Bond Strength (ASTM D-4541)	Concrete Failure
Volume Solids	100%

STORAGE & INSTALLATION

Storage Environment.....	Dry area, 40°F
Application Temperature, ambient	0–85°F
Application Temperature, substrate	Minimum 5°F above dew point
Shelf Life	1 year
Pot Life	@ 77°F: 5 min / @ 35°F: 10 min / @ 0°F: 20 min
Foot Traffic	@ 77°F: 45 min / @ 35°F: 3 hrs / @ 0°F: 20 hrs
Full Service	@ 77°F: 4 hrs / @ 35°F: 24 hrs / @ 0°F: 72 hrs

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

CONSIDERATIONS & LIMITATIONS

1. This product is not designed for exterior use, immersion, or any use where moisture can reach the underside of the flooring.
2. PolySpec recommends the use of a slip resistant grit with this product.
3. Floors should be sloped to drain to prevent standing water or chemicals. As with any surface, all spills should be removed as soon as possible to prevent a slipping hazard.
4. Do not thin with solvents unless advised to do so by PolySpec.
5. Confirm product performance in specific chemical environment prior to use.
6. Prepare substrate according to “Surface Preparation” portion of this document.
7. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
8. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
9. For industrial/commercial use. Installation by trained personnel only.

TuffRez[®] 212

TECHNICAL DATA SHEET

Epoxy Coating, Low Temperature

BENEFITS

- Cures at temperatures as low as 0°F
- Rapid set for higher temperature applications (60–85°F)
- 100% solids
- Meets USDA requirements
- Low odor during application

RECOMMENDED USES

- Cold storage rooms
- Freezers & meat lockers
- Other low temperature environments
- Environments at standard room temperature (60–85°F) that require fast set with low odor

GENERIC DESCRIPTION

Modified Epoxy

STANDARD COLORS

Light Gray

PACKAGING

1-Gallon Unit

COVERAGE

80 ft² / gallon @ 20 mils

SURFACE PREPARATION

Concrete: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.*
- *All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.*
- *Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*

Steel: For steel surfaces, a “Near White Metal” ultra high-pressure wash or abrasive blast with anchor profile of 2–4 mils in accordance with Steel Structures Painting Council Specification SP-10 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details.

INSTALLATION STEPS

NOTE: For low temperature applications, ensure that product is properly conditioned prior to use.

1. If temperature is above 45°F and time allows, prime surface with PolySpec Primer. See technical data sheet for application details.
2. Component A Resin should be premixed prior to using due to possible separation that may occur during transportation and storage.
3. Combine Component A Resin and Component B Hardener in a separate mixing vessel. IMMEDIATELY mix well with a mechanical jiffy-type mixer operated at low speed.

NOTE: Work quickly! Material has a very short pot life.

4. OPTIONAL STEP:

For use as a mortar:

- a. Pour catalyzed liquid into a concrete or mortar mixer. Add F-3 powder (75 lbs per gallon of binder) and mix thoroughly until all particles are wetted out.
 - b. Apply mortar coat with a screed box or a rake set at the appropriate height. Finish quickly using a steel finishing trowel.
5. Immediately spread epoxy onto concrete with a squeegee and backroll.
 6. OPTIONAL STEP: When applied as a non-skid coating, broadcast clean, dry 20/40-mesh sand or aluminum oxide aggregate into surface while binder is wet.
- NOTE: Do not broadcast aggregate into the prime coat.*
7. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

1.2R:1H / DOC TR212-TDS

Rev 01/10

TuffRez and PolySpec are ® Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.