

DESCRIPTION

TuffRez 240 is a 100% solids, chemical resistant epoxy liner used for protection of concrete and steel from chemicals and wastewater in immersion and splash and spillage conditions.

TYPICAL APPLICATION

Rough Concrete	
• One Coat	TuffRez 240 @ 100 mils
Smooth Concrete / Steel	
• Basecoat	TuffRez 240 @ 15-20 mils
• Topcoat	TuffRez 240 @ 15-20 mils

PERFORMANCE DATA

Compressive Strength (ASTM C-579)	12,870 psi
Tensile Strength (ASTM D-638)	6,690 psi
Flexural Strength (ASTM C-580)	12,443 psi
Bond Strength (ASTM D-4541)	450 psi
VOC	0.0 lb/gal; 0.0 gm/L
Volume Solids	100%

STORAGE & INSTALLATION

Storage Environment	Dry area, 55–95°F
Application Temperature, ambient	40–85°F
Application Temperature, substrate	Minimum 5°F above dew point
Shelf Life	1 year
Pot Life, @ 77°F	60 minutes
Tack Free, @ 70°F	8 hours
Full Service, @ 77°F	24 hours

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

CONSIDERATIONS & LIMITATIONS

1. Do not thin with solvents unless advised to do so by PolySpec.
2. Confirm product performance in specific chemical environment prior to use.
4. Prepare substrate according to “Surface Preparation” portion of this document.
5. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
6. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
7. For industrial/commercial use. Installation by trained personnel only.

TuffRez[®] 240

TECHNICAL DATA SHEET

Epoxy Liner, Chemical Resistant

BENEFITS

- Excellent resistance to dilute acids, alkalis, wastewater and sewer gas (H₂S)
- Low blush amine
- May be applied at 100 mil thickness (two 50 mil coats for vertical surfaces)

RECOMMENDED USES

- Manholes
- Large diameter sewer pipe
- Lift station walls
- Tanks

GENERIC DESCRIPTION

Epoxy

STANDARD COLORS

Gray

PACKAGING

10-Gallon Unit (special order / minimum)
4-Gallon Unit

COVERAGE

16 ft² / gallon @ 100 mils
100 ft² / gallon @ 16 mils

SURFACE PREPARATION

Concrete: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.*
- *All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.*
- *Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*

Steel: For immersion service, "white Metal" abrasive blast with an anchor profile of 2-4 mils in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, "Near White" SP-10-63 or NACE No. 2 is required.

Refer to PolySpec Surface Preparation Guidelines for more details.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.

INSTALLATION STEPS

1. Under optimum conditions, TuffRez 240 requires no priming. If a primer is necessary, prime concrete surfaces with PolySpec 100EX Primer or American Safety MS 11CZLT to hold blast on steel surfaces. See data sheet for application details.
2. Pour Component A Resin into Component B Hardener and mix with a mechanical jiffy-type mixer operated at low speed until a uniform blend is attained, normally 3 minutes.
3. Apply by brush, roller or spray.

NOTE: Recommended spray equipment is a 68:1 airless sprayer with reverse-a-clean tips, orifice size of 0.031" – 0.035". The addition of up to 10% toluene can be used to aid the application properties.

4. Multiple coats can be applied within 12 hours of the previous coat. Material is tack-free within 8 hours @ 70°F. Maximum recoat @ 75°F is 48 hours.

NOTE: If the first coating becomes, glossy and/or hard to the touch, a light sanding followed by a wipe with a 50:50 mixture of water and isopropanol will be necessary before applying the second coat. Allow the solvent to flash before applying coating.

5. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

1R:1H C / DOC TR240-TDS

Rev 07/10

TuffRez and PolySpec are © Registered Trademarks of PolySpec L.P.

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.